



NOKORODE® 95/5 PRE-TINNING PASTE FLUX

[Description](#) | [Characteristics](#) | [Applications](#) | [Packaging](#) | [Instructions](#) | [Precautions](#) | [Specifications](#) | [Limited Warranty](#)

DESCRIPTION:

Nokorode® Pre-Tinning Paste Flux is a creamy-smooth paste specifically formulated with a small amount of 95/5 tin/antimony solder powder in the formula and a heat indicator. It is formulated to clean, pretin and flux the joint all at one time. Provides a fast, safe method of fluxing most common metals and solders. Excellent for use on larger diameters fittings or faster solderings of smaller diameter fittings because it automatically tins before reaching higher temperature.



[Top of Page](#)

CHARACTERISTICS:

- Produces excellent, leak-free soldered joints
- Lead-free. Formula is safe for use on potable systems
- Cleans, Pre-tins and fluxes
- VERY low scorching or burning
- VERY low corrosive properties prevents pitting
- VERY low spattering
- Excellent wetting ability allows solder to flow easily and uniformly into joints
- Smooth stable paste for easy brush on application
- Contains small amount of 95/5 solder powder
- Excellent for larger diameter fittings or faster soldering of small diameter fittings

[Top of Page](#)

APPLICATIONS:

Nokorode® Pre-tinning Paste Flux is recommended for 95/5 or 50/50 solder applications. Can be used on common metals including copper, tin, zinc, nickel, and sheet lead. Do not use on magnesium or aluminum.

[Top of Page](#)

PACKAGING:

| Code | Size | Qty. Per Case | Lbs. per Case | Cu. Ft Per Case |
|-------|----------------------|---------------|---------------|-----------------|
| 14114 | 1.7 oz. | 48 jars | 8 | 0.35 |
| 14115 | 8 oz. (brush in cap) | 24 jars | 16 | 0.50 |
| 14116 | 4 oz. | 24 jars | 8 | 0.25 |
| 14119 | 1 lb. | 12 jars | 14 | 0.45 |

[Top of Page](#)

INSTRUCTIONS:

1. Remove all dirt from surfaces to be soldered.
2. **Do not breathe vapors during soldering operations.**
3. Apply a small amount of flux evenly to both joining surfaces. Heat and apply solder in normal manner.
4. When joint has cooled, wipe outside and flush inside surfaces thoroughly with water.
5. Flux paste may liquefy if stored in very hot conditions (usually greater than 120 degree F). Before using, cool slightly until flux re-solidifies.

For additional technical information, call Toll Free 1-800-231-3345.

[Top of Page](#)

PRECAUTIONS:

FOR CHEMICAL EMERGENCY, SPILL, LEAK, FIRE, EXPOSURE OR ACCIDENT,
CALL CHEMTREC - DAY OR NIGHT 1-800-424-9300

CAUTION!

MAY CAUSE SKIN AND EYE IRRITATION - HARMFUL IF SWALLOWED

CONTAINS: Zinc Chloride and Ammonium Chloride. PRECAUTIONS: May cause irritation to eyes, skin, digestive or respiratory system. Avoid direct contact, breathing of fumes, and ingestion. Wear adequate protective clothing and equipment. Use only with good ventilation. Wash thoroughly after use. **FIRST AID:** For any overexposure, get immediate medical attention after first aid is given. **Eyes** - Flush with clean water for 15 minutes. **Skin** - Wash with soap and water. **Inhalation** - Remove to fresh air. **Ingestion** - DO NOT INDUCE VOMITING. Only if conscious, give large amounts of water. **FIRE AND SPILLS:** For fire, use water fog, CO₂, foam, or dry chemicals. Wipe up spills to prevent footing hazard. **STORAGE AND HANDLING:** Store in cool area. Keep container tightly closed. Do not reuse empty container. **KEEP OUT OF REACH OF CHILDREN.**

For additional information, refer to Material Safety Data Sheet.

[Top of Page](#)

SPECIFICATIONS:

Wt/Gal @ 77 degree F 8.84 +- .5 lbs/gal.
Flash Point SETA CC >399 degree F
Color Tan/gold to black paste
Shelf Life 2 year minimum

Suggestions and recommendations covering the use of our products are based on our past experience and laboratory findings. However, as we have no control as to the methods and conditions of application, we only assume responsibility for the uniformity of our products within manufacturing tolerances.

[Top of Page](#)

LIMITED WARRANTY:

RectorSeal® makes the Limited Express Warranty that when the instructions for storage and handling of our products are followed we warrant our products to be free from defects. THIS LIMITED EXPRESS WARRANTY IS EXPRESSLY IN LIEU OF ANY OTHER EXPRESS OR IMPLIED WARRANTIES, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, AND OF ANY OTHER OBLIGATION ON THE PART OF RECTORSEAL®. The sole remedy for breach of the Limited Express Warranty shall be the refund of the purchase price. All other liability is negated and disclaimed, and RectorSeal® shall not be liable for incidental or consequential damages.

[Top of Page](#)

MANUFACTURED IN U.S.A. BY

RectorSeal®

2601 Spenwick Drive • Houston, TX 77055 USA

713-263-8001 • Fax 713-263-7577

Toll-free 800-231-3345 • Fax 800-441-0051

[Back](#)